



Initial list of Declarations of Performance by Product Families.

Additional Declarations of Performance are available on request.

nw = not worse than

Short code	Product	U Value declared
CGG01/59	clear/6-20 air/clear	nw 3.3
CGG T 01/59	as above toughened	nw 3.3
CGG02/59	clear/6-12 air/Planitherm Total +	nw 2.5
CGG T 02/59	as above toughened	nw 2.5
CGG03/59	clear/14-20 air/Planitherm Total +	nw 1.5
CGG T 03/59	as above toughened	nw 1.5
CGG04/59	clear/8-10 argon/Planitherm Total +	nw 1.7
CGG T 04/59	as above toughened	nw 1.7
CGG05/59	clear/12 argon/Planitherm Total +	nm 1.3
CGG T 05/59	as above toughened	nw 1.3
CGG06/59	clear/14-20 argon/Planitherm Total +	nw 1.2
CGG T 06/59	as above toughened	nw 1.2
CGG07/59	clear/8-10 argon/Planitherm One 11	nw 1.6
CGG T 07/59	as above toughened	nw 1.6
CGG08/59	clear/12 argon/Planitherm One 11	nw 1.2
CGG T 08/59	as above toughened	nw 1.2

CGG09/59	clear/14 18 20 argon/Planitherm One 11	nw 1.1
CGG T 09/59	as above toughened	nw 1.1
CGG10/59	clear/16 Argon/Planitherm One 11	nw 1.0
CGG T 10/59	as above toughened	nw 1.0
CGG T 11/59	6mm toughened SKN 174/ 12 argon/6mm clear toughened	nw 1.3
CGG T 12/59	6mm toughened SKN 174/14-20 argon/6mm clear toughened	nw 1.1
CGG T 13/59	6mm toughened SKN 165/12 argon/6mm clear toughened	nw 1.2
CGG T 14/59	6mm toughened SKN 165/14 18 20 argon/6mm clear toughened	nw 1.1
CGG T 15/59	6mm toughened SKN 165/16 argon/6mm clear toughened	nw 1.0
CGG T 16/59	6mm toughened SKN 154/12 argon/6mm clear toughened	nw 1.2
CGG T 17/59	6mm toughened SKN 154/14 18 20 argon/6mm clear toughened	nw 1.1
CGG T 18/59	6mm toughened SKN 154/16 argon/6mm clear toughened	nw 1.0
CGG 19/59	clear/8-12 argon/Pilkington k	nw 2.0
CGG T 19/59	as above toughened	nw 2.0
CGG20/59	clear/14-20 argon/Pilkington k	nw 1.5
CGG T 20/59	as above toughened	nw 1.5
CGG21/59	clear/6-20 air/Pilkington k	nw 2.7
CGG T 21/59	as above toughened	nw 2.7
CGG22/59	clear/8-12 argon/Pilkington k OW	nw 2.0
CGG T 22/59	as above toughened	nw 2.0
CGG23/59	clear/14-20 argon/Pilkington k OW	nw 1.5
CGG T 23/59	as above toughened	nw 1.5
CGG24/59	clear/6-20 air/Pilkington k OW	nw 2.7
CGG T 24/59	as above toughened	nw 2.7
CGG T 25/59	Pilkington Activ Blue toughened/14-20 argon/ soft coat toughened	nw 1.2
CGG T 26/59	Pilkington Activ Neutral toughened/14-20 argon/ soft coat toughened	nw 1.2
CGG27/59	clear/8 argon/Planitherm Total + toughened/8 argon/Planitherm Total +	nw 1.0

CGG T 27/59	as above toughened	nw 1.0
CGG28/59	clear/12 argon/Planitherm Total + toughened/12 argon/Planitherm Total +	nw 0.8
CGG T 28/59	as above toughened	nw 0.8
CGG29/59	clear/16 argon/Planitherm Total +/16 argon/Planitherm Total +	nw 0.6
CGG T 29/59	as above toughened	nw 0.6
CGG T 30/59	clear toughened/8 argon/Planitherm One 11/8 argon/Planitherm One 11	nw 0.9
CGG T 31/59	clear toughened/12 argon/Planitherm One 11/12 argon/Planitherm One 11	nw 0.7
CGG T 32/59	clear toughened/16 argon/Planitherm One 11/16 argon/Planitherm One 11	nw 0.5
CGG33/59	Heritage clear/4-6 air/clear	nw 3.6
CGG T 33/59	as above toughened	nw 3.6
CGG34/59	Heritage clear/4-6 argon/Planitherm Total +	nw 2.6
CGG T 34/59	as above toughened	nw 2.6
CGG35/59	Heritage clear/4 krypton/Planitherm Total +	nw 1.9
CGG T 35/59	as above toughened	nw 1.9
CGG36/59	Heritage clear/6 krypton/Planitherm Total +	nw 1.5
CGG T 36/59	as above toughened	nw 1.5

Cornwall Glass & Glazing Ltd

Stennack Road, Holmbush Industrial Estate, St Austell, PL25 3JQ 01726 66325

[www.cornwallglass.co.uk](http://www.cornwallglass.co.uk)